
BETONCORD®/40



Concrete hose
for wet cement, concrete, plaster and other wet abrasive materials.

Marking: Betoncord® Concrete / Beton PN 40 bar

Norm	EN ISO 1307:2008 ISO 4649 (previous DIN 53516)
WP	40 bar
BP	120 bar
Min. temperature	-35°C
Max. temperature	+80°C
Electr. resistance tube	Electrical conductive $<10^6 \Omega$
Electr. resistance cover	Antistatic $<10^9 \Omega$
Electr. resistance tube to cover	Antistatic $<10^9 \Omega$
Electrical resistance acc. norm	EN ISO 8031:2009
Compound tube	SBR/NR
Abrasion value tube	70 mm ³
Construction tube	Smooth
Color tube	Black
Compound cover	SBR
Construction cover	Fabric finish
Color cover	Black
Reinforcements	Textile plies

Art.no.	Ø Inner mm	Wall mm	Ø Outer mm	Bendingradius mm	Weight/mtr	Length mtr.
ACEBE025	25	7,0	39	250	0,840 kg	40
ACEBE035	35	7,0	49	350	1,150 kg	40
ACEBE038	38	8,0	54	380	1,480 kg	40
ACEBE050	50	9,0	68	500	1,950 kg	40
ACEBE065	63,5	11,0	85,5	650	2,920 kg	40

Application: Suitable for concrete mortar and other wet abrasive materials such as grouting mortar, plaster, plaster mortar and others. The hose can also be used for dry substances such as cement and blasting grit. Very long lifespan due to very thick wear resistant tube and cover. The hose is kink-resistant due to the special compact construction of the insertions. This allows the hose to be used at high working pressures.